

Dolomite and limestone cement

Experimental results and thermodynamic modelling

Maciej Zajac




Mohsen Ben Haha

4th GEMS Workshop, Dübendorf

May 8th 2014

Outline

- Background
- Results (Portland dolomite cement)
 - Mechanical performance
 - Hydration
 - Phases assemblage: modelling and experimental results
 - Microstructure
- Conclusion




Background

Dolomite as a supplementary cementitious material

- ➔ properties not well investigated as for other composite cement systems

Alkali carbonate reaction





- Potential expansion

Impact of magnesium on hydration

- Impact on the kinetics of hydration
- Stable phase composition
- Impact on the hydrates composition

Mechanical performance

- Similar compressive strength of PLC and PDC
- Higher temperature reduces final strength





Hydration

■ Similar reaction rate of PLC and PDC

- No strong effect of Mg after 1 day

■ Strong acceleration by temperature




Slide 5 – 10-04-2014
MZA – Dolomite cement

**HEIDELBERG
TECHNOLOGY CENTER**
HEIDELBERGCEMENT Group

Hydration

■ Temperature accelerates dissolution of dolomite

- 20°C – reaction limited at 180 days
- 60°C – 90% of dolomite dissolves at 180 days




Slide 6 – 10-04-2014
MZA – Dolomite cement

**HEIDELBERG
TECHNOLOGY CENTER**
HEIDELBERGCEMENT Group

Phase assemblage at 40°C

- No significant differences, low reaction degree of dolomite




Slide 7 – 10-04-2014
MZA – Dolomite cement

HEIDELBERG
TECHNOLOGY CENTER
HEIDELBERG CEMENT Group

Phase assemblage at 60°C

- Magnesium bounds alumina to form hydrotalcite





Slide 8 – 10-04-2014
MZA – Dolomite cement

HEIDELBERG
TECHNOLOGY CENTER
HEIDELBERG CEMENT Group

Phase assemblage, effect of temperature

Temperature changes the phase assemblage

- AFt not stable above ~ 50°C





Slide 9 – 10-04-2014
MZA – Dolomite cement

HEIDELBERG
TECHNOLOGY CENTER
HEIDELBERGCEMENT Group

Phase assemblage, effect of temperature

Dolomite changes the phase assemblage

- AFm → Hydrotalcite ($\text{Mg}_4\text{Al}_2\text{O}_7 \cdot 10\text{H}_2\text{O}$)
- Modelling does not predict correctly ($\text{Mg}/\text{Al} > 2$, AFt less stable than Ht?)




Slide 10 – 06-02-2014
MZA – Dolomite cement

HEIDELBERG
TECHNOLOGY CENTER
HEIDELBERGCEMENT Group

Microstructure

■ Partially / fully reacted dolomite grains at 60°C



Slide 11 – 06-02-2014
MZA – Dolomite cement

**HEIDELBERG
TECHNOLOGY CENTER**
HEIDELBERGCEMENT Group

Conclusions

- Compressive strength similar for PLC and PDS systems
- Dolomite is not thermodynamically stable and dissolves in cement matrix
 - Process is very slow at 20°C
- Main hydration product of dolomite is hydrotalcite in cement matrix
 - Presence of brucite not confirmed
- Magnesium react strongly with alumina
 - Decrease of Al/Si ratio of C-S(A)-H
 - Destabilization of AFm

Slide 12 – 10-04-2014
MZA – Dolomite cement

**HEIDELBERG
TECHNOLOGY CENTER**
HEIDELBERGCEMENT Group



For better building

**HEIDELBERG
TECHNOLOGY CENTER**
HEIDELBERGCEMENT Group

